

PROCESS FOR TREATING PREVIOUSLY COATED PHOSPHOR PARTICLES

ABSTRACT

Particles of electroluminescent phosphor having a moisture proof coating are re-coated by treating the phosphor in a fluidized bed with a mixture of water vapor
5 and an organotrichlorosilane compound for approximately thirty minutes. The resultant siloxane coating further improves the moisture resistance of the phosphor.